PENTENS CUREHARD MY

Hardening Compound/Curing

Product Data Sheet

Description

PENTENS CUREHARD MY is a liquid applied, styrene acrylic clear resin. It is designed to give superior resistance to water retention for newly freshly placed concrete. PENTENS CUREHARD MY impregnate and penetrate within the concrete surface which provides good wear resistant.

Uses

On freshly-placed concrete:

- Floor hardener
- Curing compound

On hardened concrete:

- Floor hardener

Advantages

- Seals moisture in freshly placed concrete for curing and provides a hard and dust-free surface.
- The dry coating resists oil, grease, stain and short exposure to gasoline.
- On hardened concrete, it impregnates into the concrete making it easy to clean and maintain the floor.
- Easy to apply and dries quickly.

Technical & Physical Data

Form	Clear liquid
Specific Gravity (25°C)	0.88
Consumption	On freshly-placed concrete ~ 5 m^2/litre On dry, hardened concrete ~ 10 m^2/litre/coat (2 coats required)
Shelf Life and Storage	1 year from the date of production when stored in original unopened packaging in a cool, dry place
Packaging	20 kg/pail 200 kg/drum

Important Note

The material must be stored indoor to avoid being exposed to direct sunlight, wind or rain. Keep the material away from fire or smoke.

Disclaimer. All representations and recommendations set forth are given in good faith and to the best of our knowledge. However due to varying conditions and applications, the buyer shall conduct its own tests of this product before use. Under no circumstances will the manufacturer be liable for any loss or damages caused by incorrect usages. The sale of this product shall be on terms and conditions set forth on Pentens order acknowledgement.

Instruction for Use

As a curing agent
Apply PENTENS CUREHARD MY with a low pressure spray gun immediately after concrete finishing.

As a hardener
After 28 days of the casting of the concrete (depending on the curing conditions), apply 1 – 2 coats of PENTENS CUREHARD MY on the dry surface with a roller, spray or brush.

Safety

Impervious gloves and barrier cream should be used when handling these products. Eye protection should be worn. In case of contact with eyes, rinse thoroughly with plenty of water and seek medical advice if symptoms persist. If contact with skin occurs, it must be removed before curing takes place. Wash off with an industrial skin cleanser followed by plenty of soap and water. Do not use solvent. Ensure adequate ventilation when using these products.

UFON NANO-CHEMICAL LTD.
8F, No.2, Lane 348, Sec 2, Chung-Shang Road,
Chung Ho City, Taipei Hsien, Taiwan, R.O.C.
Tel: +886 2 2240 0220 Fax: +886 2 2242 6536
URL: www.pentens.com
E-mail: pentens@ms35.hinet.net

DONG JI (M) SDN. BHD.
No.8, Jalan TPP 5/7, Taman Perindustrian Puchong,
47100 Puchong Selangor, Malaysia.
Tel: +603 8060 4396 Fax: +603 8060 4394
URL: www.pentens.com.my
E-mail: dji@pentens.com.my